

WHAT IS CLAIMED IS:

1. A paint for forming an insulating film on an inorganic material, the inorganic material being at least one selected from glass, ceramic, and a metal compound, comprising:
  - inorganic fine particles (a);
  - a binder resin (b); and
  - a solvent (c) that forms a contact angle of less than 5° with the inorganic material.
2. A paint for forming an insulating film according to claim 1, wherein the inorganic material contains glass, ceramic, and a metal compound.
3. A paint for forming an insulating film according to claim 1, wherein the glass is a glass substrate, the ceramic is an ITO film, and the metal compound is a metal electrode.
4. A paint for forming an insulating film according to claim 1, wherein the solvent (c) contains 50 wt. % or more of at least one solvent selected from diethyl carbitol, dipropylene glycol-n-propyl ether, tripropylene glycol monomethyl ether, diethyl cellosolve, carbitol acetate, dibutyl cellosolve, and propylene glycol diacetate.
5. A paint for forming an insulating film according to claim 1, wherein the solvent (c) contains 50 wt. % or more of at least one solvent selected from diethyl carbitol, dipropylene glycol-n-propyl ether, tripropylene glycol monomethyl ether, and diethyl cellosolve.
6. A paint for forming an insulating film according to claim 1, wherein the solvent (c) contains at least two solvents selected from diethyl carbitol, dipropylene glycol-n-propyl ether, tripropylene glycol monomethyl ether, and diethyl cellosolve.
7. A paint for forming an insulating film according to claim 1, wherein the inorganic fine particles (a) are at least one selected from SiO<sub>2</sub>, ZnO, B<sub>2</sub>O<sub>3</sub>, PbO, Bi<sub>2</sub>O<sub>3</sub>, BaO, P<sub>2</sub>O<sub>5</sub>, CaO, SrO, and MgO.

8. A paint for forming an insulating film according to claim 1,  
wherein the binder resin (b) is at least one selected from a cellulosic resin, an acrylic resin, polyvinyl alcohol, and polyvinyl butyral.

5 9. A paint for forming an insulating film according to claim 1 comprising:  
10 to 95 wt. % of the inorganic fine particles (a);  
1 to 20 wt. % of the binder resin (b); and  
4 to 85 wt. % of the solvent (c).

10 10. A method of manufacturing a plasma display panel comprising:  
coating a paint for forming an insulating film onto a member of a  
plasma display panel, the paint comprising inorganic fine particles (a), a  
binder resin (b), and a solvent (c) that forms a contact angle of less than 5°  
with an inorganic material; and  
15 firing the paint to form an insulating film on the member.

11. A method of manufacturing a plasma display panel according to claim 10,  
wherein the member is a back plate of a plasma display panel, which  
is provided with address electrodes, and the insulating film serves as an  
20 address electrode protective film.

12. A method of manufacturing a plasma display panel according to claim 10,  
wherein the member is a back plate of a plasma display panel and the  
insulating film serves as partition walls.  
25

13. A method of manufacturing a plasma display panel according to claim 10,  
wherein the member is a front plate of a plasma display panel, which  
is provided with display electrodes, and the insulating film serves as a  
dielectric layer.  
30

14. A method of manufacturing a plasma display panel according to claim 10,  
wherein the member is cleaned by ultraviolet cleaning before being  
coated with the paint.

35 15. A plasma display panel comprising:  
an insulating film that is obtained by coating a paint for forming an  
insulating film onto an inorganic material, the paint comprising inorganic fine

particles (a), a binder resin (b), and a solvent (c) that forms a contact angle of less than 5° with the inorganic material.

5 16. A plasma display panel according to claim 15,  
wherein the insulating film serves as an address electrode protective film.

17. A plasma display panel according to claim 15,  
wherein the insulating film serves as partition walls.

10 18. A plasma display panel according to claim 15,  
wherein the insulating film serves as a dielectric layer.

09975687-101094